



DATENBLATT

KAOLINTON : TS II

Chemische Analyse :

SiO ₂	73,70 %
Al ₂ O ₃	21,80 %
TiO ₂	0,28 %
Fe ₂ O ₃	1,03 %
CaO	0,03 %
MgO	0,13 %
Na ₂ O	0,07 %
K ₂ O	2,25 %
Glühverlust (1110 C)	6,50 %
Fluor	0,02 %
Brennfarbe	weiß-creme

Mineralanalyse

Tonsubstanz (Kaolin)	:	46 %
Feldspat	:	2 %
Glimmer	:	7 %
Quarz	:	43 %